

1. Identification of the substance/mixture and of the company/undertaking

Manufacturer: E. I. du Pont de Nemours and Company.
 DuPont Performance Coatings
 Wilmington, DE 19898

Telephone: Product information: (800) 441-7515
 Medical emergency: (800) 441-3637
 Transportation emergency: (800) 424-9300 (CHEMTREC)

Product: **Mastertint® and Mastertint® Specialty Additives**

DOT Shipping Name: See DOT Addendum.

Hazardous Materials Information: See Section 10.

Copyright 2011 E. I. du Pont de Nemours and Company. All rights reserved. Copies may be made only for those using DuPont products.

2. Composition/information on ingredients

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
1,2,4-trimethyl benzene	96591-17-2	None	A None, O None
2-methyl butyl acetate	95-63-6	7.0@44.4 °C	A 25.0 ppm, O 25.0 ppm
Acetone	624-41-9	None	A 100.0 ppm 15 min STEL, A 50.0 ppm, O None
	67-64-1	247.0@68.0 °F	A 750.0 ppm 15 min STEL, A 500.0 ppm, O 1000.0 ppm, D 500.0 ppm 8 & 12 hour TWA
Acrylic polymer	148969-95-3	None	A None, O None
Aluminum	7429-90-5	None	O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, D 0.5 mg/m3 8 & 12 hour TWA, A None
Aluminum benzoate	555-32-8	None	A 15.0 mg/m3 Metal Dust Al, O 15.0 mg/m3 Metal Dust Al
Aluminum hydroxide	21645-51-2	None	A 1.0 mg/m3, O None
Aluminum oxide	1344-28-1	None	O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, A None
Amorphous silica	7631-86-9	None	A 3.0 mg/m3 Respirable Dust, O 20.0 mppcf, D 3.0 mg/m3, D 6.0 mg/m3
Aromatic hydrocarbon-A	64742-94-5	10.0	D 100.0 ppm, A None, O None
Aromatic hydrocarbon-B	64742-95-6	10.0@25.0 °C	D 50.0 ppm, A None, O None
Azomethine copper-complex	15680-42-9	None	A None, O None
Barium sulfate	7727-43-7	None	O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, D 10.0 mg/m3 Total Dust, D 5.0 mg/m3 8 & 12 hour TWA Respirable Dust, A None
Butyl acetate	123-86-4	10.0	A 200.0 ppm 15 min STEL, A 150.0 ppm, O 150.0 ppm
C.i. pigment blue 60	81-77-6	None	A None, O None
C.i. pigment brown	6992-11-6	None	A None, O None
C.i. pigment red 254	84632-65-5	None	A None, O None
C.i. pigment yellow 154	68134-22-5	None	A None, O None
Calcined kaolin	66402-68-4	None	A 3.0 mg/kg Respirable Dust, A 10.0 mg/m3 inhalable dust, O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust
Carbazole violet pigment	6358-30-1	None	A None, O None
Carbon black	1333-86-4	None	A 3.0 mg/m3, O 3.5 mg/m3, D 0.5 mg/m3 8 & 12 hour TWA
Cellulose acetate butyrate	9004-36-8	None	A None, O None
Cumene	98-82-8	3.7	A 50.0 ppm, O 50.0 ppm Skin
Ethylbenzene	100-41-4	7.0	A 20.0 ppm, O 100.0 ppm, D 25.0 ppm 8 & 12 hour TWA
Ethylene glycol monobutyl ether	111-76-2	0.6	A 20.0 ppm, O 50.0 ppm Skin, D 20.0 ppm 8 & 12 hour TWA
Graphite	7782-42-5	None	A 2.0 mg/m3 Respirable Dust, O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust
Heavy mineral spirits	64741-65-7	10.0@25.0 °C	D 100.0 ppm, A None, O None
Hydrotreated heavy naphtha (petroleum)	64742-48-9	0.7@68.0 °F	A 100.0 ppm, O 500.0 ppm, D 100.0 ppm
Iron oxide	1309-37-1	None	A 5.0 mg/m3 Respirable Dust, O 10.0 mg/m3, D 3.0 mg/m3
Isoindolinone pigment	36888-99-0	None	A None, O None
Isoindolinone yellow pigment	106276-79-3	None	A None, O None
Light yellow lemon yellow oxide pigment	51274-00-1	None	A None, O None
Methyl methacrylate	80-62-6	28.0	A 100.0 ppm 15 min STEL, A 50.0 ppm, O 100.0 ppm
Mica	12001-26-2	None	A 3.0 mg/m3 Respirable Dust, O 20.0 mppcf, O 3.0 mg/m3 Respirable Dust

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Monoazo pigment	12236-62-3	None	A 10.0 mg/m3 inhalable dust particulate, O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust
Naphthalene	91-20-3	1.0@52.6 °C	A 15.0 ppm CEIL Skin, A 10.0 ppm Skin, O 10.0 ppm, D 0.1 ppm 8 & 12 hour TWA
Perylene maroon	5521-31-3	None	A None, O None
Perylene pigment	5521-31-3	None	A 10.0 mg/m3, O None
Phthalocyanine blue	29719-96-8	None	A 10.0 mg/m3, O 5.0 mg/m3 Respirable Dust, O 15.0 mg/m3
Phthalocyanine blue pigment	147-14-8	None	A 10.0 mg/m3 inhalable dust PNOC, A 3.0 mg/m3 respirable particulate PNOC, O 15.0 mg/m3 Total Dust PNOR, O 5.0 mg/m3 TWA Respirable Dust PNOR
Phthalocyanine green	1328-53-6	None	A 3.0 mg/m3 TWA Respirable Dust, A 10.0 mg/m3 TWA inhalable dust, O 15.0 mg/m3 TWA Total Dust, O 5.0 mg/m3 TWA Respirable Dust
Phthalocyanine green pigment	68512-13-0	None	A None, O None
Pigment red 202	3089-17-6	None	A 3.0 mg/m3 Respirable Dust, A 10.0 mg/m3 inhalable dust PNOR, O 5.0 mg/m3 Respirable Dust PNOR, O 15.0 mg/m3
Polyethylene/vinyl acetate	24937-78-8	None	A None, O None
Polyoxyalkylenes	104376-75-2	None	A None, O None
Primary amyl acetate	628-63-7	4.2	A 100.0 ppm 15 min STEL, A 50.0 ppm, O 100.0 ppm
Proprietary copper compound	NotAvail	None	A None, O None
Propylene carbonate	108-32-7	0.0	A None, O None
Quinacridone magenta	980-26-7	None	A None, O None
Quinacridone pigment	1047-16-1	None	A 10.0 mg/m3 inhalable dust, A 3.0 mg/m3, O 15.0 mg/m3 Total Dust PNOR, O 5.0 mg/m3 Respirable Dust, D 10.0 mg/m3 Total Dust
Red iron oxide light	1332-37-2	None	A 10.0 mg/m3 PNOR, A 3.0 mg/m3 Respirable Dust, A 5.0 mg/m3 Fe, O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust
Stoddard solvent	8052-41-3	1.0@25.0 °C	A 100.0 ppm, O 500.0 ppm TWA, D 100.0 ppm 15 min STEL, D 50.0 ppm 8 & 12 hour TWA
Substituted pyrrolpyrrol	54660-00-3	None	A None, O None
Tetrachloroisosolinone yellow pigment	5590-18-1	None	A 250.0 ppm, O None
Tin oxide	18282-10-5	None	A 2.0 mg/m3, O 2.0 mg/m3
Titanium dioxide	13463-67-7	None	O 15.0 mg/m3 Total Dust, D 10.0 mg/m3 Total Dust, D 5.0 mg/m3 Respirable Dust, A None
Titanium dioxide (rutile)	1317-80-2	None	A 10.0 mg/m3 TWA Total Dust, O 10.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, D 10.0 mg/m3 Total Dust, D 5.0 mg/m3 Respirable Dust
Weather resistant mixture	NotAvail	None	A None, O None
Xylene	1330-20-7	8.0@25.0 °C	A 150.0 ppm 15 min STEL, A 100.0 ppm, O 100.0 ppm, D 150.0 ppm 15 min STEL, D 100.0 ppm 8 & 12 hour TWA
Yellow iron oxide	51274-00-1	None	A 10.0 mg/m3, O 15.0 mg/m3
Zirconium oxide	1314-23-4	None	A 10.0 mg/m3 15 min STEL, A 5.0 mg/m3, O 5.0 mg/m3 Zr

*A=ACGIH, O=OSHA, D=DuPont, S=Suppliers. Limits are 8 hour TWA unless otherwise specified. Vapor pressure @ 20° C unless otherwise noted.

3. Hazards identification

Potential Health Effects:

Inhalation:

May cause nose and throat irritation. May cause nervous system depression, characterized by the following progressive steps: headache, dizziness, nausea, staggering gait, confusion, unconsciousness. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. If this product contains or is mixed with an isocyanate activator/hardener, the following health effects may apply: Exposure to isocyanates may cause respiratory sensitization. This effect may be permanent. Symptoms include an asthma-like reaction with shortness of breath, wheezing, cough or permanent lung sensitization. This effect may be delayed for several hours after exposure. Repeated overexposure to isocyanates may cause a decrease in lung function, which may be permanent. Individuals with lung or breathing problems or prior reactions to isocyanates must not be exposed to vapors or spray mist of this product.

Ingestion:

May result in gastrointestinal distress.

Skin or eye contact:

May cause irritation or burning of the eyes. Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis.

Other Potential Health Effects in addition to those listed above:

Acetone

The following medical conditions may be aggravated by exposure: lung disease, eye disorders, skin disorders. Overexposure may cause damage to any of the following organs/systems: blood, central nervous system, eyes, kidneys, liver, respiratory system, skin.

Aromatic hydrocarbon-A

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Aromatic hydrocarbon-B

The following medical conditions may be aggravated by exposure: skin disorders. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Butyl acetate

May cause abnormal liver function. The following medical conditions may be aggravated by exposure: respiratory system. Tests for embryotoxic activity in animals has been inconclusive. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother.

C.i. pigment yellow 154

Inhalation may cause any of the following: respiratory tract irritation. Skin or eye contact may cause any of the following: irritation.

Carbon black

Is an IARC, NTP or OSHA carcinogen. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. The following medical conditions may be aggravated by exposure: asthma, respiratory disease. WARNING: This chemical is known to the State of California to cause cancer.

Cumene

WARNING: This chemical is known to the State of California to cause cancer.

Ethylbenzene

Is an IARC, NTP or OSHA carcinogen. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, lungs. Recurrent overexposure may result in liver and kidney injury. Studies in laboratory animals have shown reproductive, embryotoxic and developmental effects. WARNING: This chemical is known to the State of California to cause cancer.

Ethylene glycol monobutyl ether

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow, central nervous system, eyes, gastrointestinal system, kidneys, liver, respiratory system, skin. May cause injury to the kidneys, liver, blood and/or bone marrow. Repeated overexposure may result in damage to the blood. Eye contact may cause corneal injury. If absorbed through the skin, may be: harmful.

Heavy mineral spirits

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Hydrotreated heavy naphtha (petroleum)

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Light yellow lemon yellow oxide pigment

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

Methyl methacrylate

The following medical conditions may be aggravated by exposure: liver disease, lung disease, respiratory disease, kidney disorders. This substance may cause effects on any of the following organs/systems: eyes, immune system, kidneys, liver, lungs, respiratory system, skin. ACGIH designates this as having potential to sensitize people as a result of dermal contact and/or inhalation exposure. Skin contact may cause any of the following: severe irritation, allergic contact dermatitis, skin sensitization. Inhalation may cause any of the following: stupor (central nervous system depression), respiratory tract irritation.

Mica

Repeated or prolonged inhalation may cause any of the following: lung irritation. Long-term respiratory exposure exceeding TLV may damage the lungs, leading to bronchitis and impairment of lung capacity.

Naphthalene

Is an IARC, NTP or OSHA carcinogen. Tests in some laboratory animals demonstrate carcinogenic activity. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: kidneys, liver. Recurrent overexposure may result in liver and kidney injury. WARNING: This chemical is known to the State of California to cause cancer.

Proprietary copper compound

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

Red iron oxide light

Long-term respiratory exposure of iron oxide may result in deposition of particles in the lung (benign siderosis).

Stoddard solvent

The following medical conditions may be aggravated by exposure: asthma, skin disorders. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Titanium dioxide

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m3 respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m3 level are not relevant to the workplace. Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium Dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.

Titanium dioxide (rutile)

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m3 respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m3 level are not relevant to the workplace. Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.

Xylene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow, cardiovascular system, central nervous system, kidneys, liver, lungs. Recurrent overexposure may result in liver and kidney injury. High exposures may produce irregular heart beats. Canada classifies Xylene as a developmental toxin as high exposures to xylenes in some animal studies have been reported to cause health effects on the developing fetus/embryo. These effects were often at levels toxic to the adult animal. The significance of these effects to humans is not known. Repeated or prolonged skin contact may cause any of the following: irritation, dryness, cracking of the skin.

4. First aid measures

First Aid Procedures:

Inhalation:

If affected by inhalation of vapor or spray mist, move to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. If breathing difficulty persists, or occurs later, consult a physician.

Ingestion:

In the unlikely event of ingestion, DO NOT INDUCE VOMITING. Call a physician immediately and have names of ingredients available.

Skin or eye contact:

In case of eye contact, immediately flush with plenty of water for at least 15 minutes; call a physician. In case of skin contact, wash thoroughly with soap and water. If irritation occurs, contact a physician.

5. Fire-fighting measures

Flash Point (Closed Cup):

See Section 11 for exact values.

Flammable Limits: LFL 1 % UFL 12.8 %

Extinguishing Media:

Universal aqueous film-forming foam, carbon dioxide, dry chemical.

Fire Fighting Procedures:

Full protective equipment, including self-contained breathing apparatus, is recommended. Water from fog nozzles may be used to prevent pressure build-up.

Fire and Explosion Hazards:

For flammable liquids, vapor/air will ignite when an ignition source is present. In other cases, when heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

6. Accidental release measures

Procedures for cleaning up spills or leaks:

Ventilate area. Remove sources of ignition. Prevent skin and eye contact and breathing of vapor. If material does not contain or is not mixed with an isocyanate activator/hardener: Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C), eye protection, gloves and protective clothing. Confine, remove with inert absorbent, and dispose of properly. If the material contains, or is mixed with an isocyanate activator/hardener: Wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C), eye protection, gloves and protective clothing. Pour liquid decontamination solution over the spill and allow to sit at least 10 minutes. Typical decontamination solutions for isocyanate containing materials are: 20% Surfactant (Tergitol TMN 10) and 80% Water OR 0-10% Ammonia, 2-5% Detergent and Water (balance). Pressure can be generated. Do not seal waste containers for 48 hours to allow CO2 to vent. After 48 hours, material may be sealed and disposed of properly.

Ecological information:

There is no data available on the product. The product should not be allowed to enter drains, water courses or the soil.

7. Handling and storage

Precautions to be taken in handling and storing:

Observe label precautions. If combustible (flashpoint between 38-93 deg C or 100 - 200 deg F), keep away from heat, sparks and flame. If flammable (flashpoint less than 38 deg C or 100 deg F), also keep away from static discharges and other sources of ignition. If material is extremely flammable (flashpoint less than - 8 deg C or 20 deg F) or flammable, VAPORS MAY IGNITE EXPLOSIVELY OR CAUSE FLASH FIRE, respectively. Vapors may spread long distances. Prevent buildup of vapors. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 49 deg C or 120 deg F. If product is waterbased, do not freeze.

Other precautions:

If material is a coating: do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves. Combustible dust clouds may be created where operations produce fine material (dust). Avoid formation of significant deposits of material as they may become airborne and form combustible dust clouds. Handling and processing operations should be conducted in accordance with best practices (e.g.NFPA-654).

8. Exposure controls/personal protection

Ventilation:

Provide sufficient ventilation in volume and pattern to keep contaminants below applicable exposure limits.

Respiratory protection:

Do not breathe vapors or mists. If this product contains isocyanates or is used with an isocyanate activator/hardener, wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C) while mixing activator/hardener with paint, during application and until all vapors and spray mist are exhausted. If product does not contain or is not mixed with an isocyanate activator/hardener, a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH TC-23C) and particulate filter (NIOSH TC-84A) may be used. Follow respirator manufacturer's directions for respirator use. Do not permit anyone without protection in the painting area. Individuals with history of lung or breathing problems or prior reaction to isocyanates should not use or be exposed vapor or spray mist if product contains or is mixed with isocyanate activators/hardeners.

Protective equipment:

Personal protective equipment should be worn to prevent contact with eyes, skin or clothing.

Skin and body protection:

Neoprene gloves and coveralls are recommended.

Desirable in all industrial situations. Goggles are preferred to prevent eye irritation. If safety glasses are substituted, include splash guard or side shields.

9. Physical and chemical properties

Evaporation rate	Slower than Ether
Water solubility	NIL
Vapour density	Heavier than air
Approx. Boiling Range (°C)	56 – 170 °C
Approx. Freezing Range (°C)	-95 °C
Gallon Weight (lbs/gal)	7.8864 - 29.1505
Specific Gravity	0.95 - 3.49
Percent Volatile By Volume	0.00 - 79.33
Percent Volatile By Weight	0.00 - 71.84
Percent Solids By Volume	20.67 - 100.00
Percent Solids By Weight	27.09 - 100.00

10. Stability and reactivity

Stability:

Stable

Incompatibility (materials to avoid):

None reasonably foreseeable

Hazardous decomposition products:

CO, CO₂, smoke, and oxides of any heavy metals that are reported in "Composition, Information on Ingredients" section.

Hazardous Polymerization:

Will not occur.

Sensitivity to Static Discharge:

For flammable materials (flashpoint less than 38 deg C or 100 deg F) and combustibles (flashpoint between 38- 93 deg C or 100-200 deg F) if heated above the flashpoint, solvent vapors in air may explode if static grounding and bonding is not used during transfer of this product.

Sensitivity to Mechanical Impact:

None known.

11. Additional Information

1001S™ Ethylene glycol monobutyl ether(10%*), Mica, Titanium dioxide(26.5%), Weather resistant mixture GAL WT: 20.75 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 76.56 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: Above 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

1002S™ Ethylene glycol monobutyl ether(10%), Iron oxide, Mica **GAL WT: 22.20 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 75.33 SOLVENT DENSITY: 7.53 VOC LE: 2.2 VOC AP: 2.2 FLASH POINT: Above 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1003S™ Ethylene glycol monobutyl ether(10%), Iron oxide, Mica, Weather resistant mixture **GAL WT: 21.60 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 71.16 SOLVENT DENSITY: 7.53 VOC LE: 2.2 VOC AP: 2.2 FLASH POINT: No measurable H: 2 F: 2 R: 0 OSHA STORAGE: N/A TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1004S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(44.0%), Weather resistant mixture **GAL WT: 21.19 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 71.74 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: Above 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1005S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(36.0%), Weather resistant mixture **GAL WT: 20.75 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 72.38 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: Above 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1006S™ Ethylene glycol monobutyl ether(10%), Iron oxide, Mica, Weather resistant mixture **GAL WT: 21.60 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 75.46 SOLVENT DENSITY: 7.53 VOC LE: 2.2 VOC AP: 2.2 FLASH POINT: Above 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1007S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(43.0%), Weather resistant mixture **GAL WT: 21.19 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 71.79 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: Above 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1009S™ Heavy mineral spirits, Mica, Titanium dioxide (rutile)(50.7%) **GAL WT: 21.60 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 73.03 SOLVENT DENSITY: 6.50 VOC LE: 2.2 VOC AP: 2.2 FLASH POINT: Above 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1010S™ Ethylene glycol monobutyl ether(10%), Iron oxide, Mica, Weather resistant mixture **GAL WT: 29.15 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 61.09 SOLVENT DENSITY: 7.53 VOC LE: 2.9 VOC AP: 2.9 FLASH POINT: No measurable H: 1 F: 2 R: 0 OSHA STORAGE: N/A TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1011S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(37.0%), Weather resistant mixture **GAL WT: 21.19 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 76.10 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: No measurable H: 2 F: 2 R: 0 OSHA STORAGE: N/A TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1012S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(55.5%), Weather resistant mixture **GAL WT: 21.28 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 71.70 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: No measurable H: 2 F: 2 R: 0 OSHA STORAGE: N/A TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1014S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(40.0%), Weather resistant mixture **GAL WT: 20.83 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 72.30 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: No measurable H: 2 F: 2 R: 0 OSHA STORAGE: N/A TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1018S™ Ethylene glycol monobutyl ether(10%), Mica, Tin oxide, Titanium dioxide(38.0%), Weather resistant mixture **GAL WT: 20.83 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 76.43 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: No measurable H: 1 F: 2 R: 0 OSHA STORAGE: N/A TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1019S™ Ethylene glycol monobutyl ether(10%), Iron oxide, Mica, Weather resistant mixture, Zirconium oxide **GAL WT: 22.47 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 70.12 SOLVENT DENSITY: 7.53 VOC LE: 2.2 VOC AP: 2.2 FLASH POINT: No measurable H: 2 F: 2 R: 0 OSHA STORAGE: N/A TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1020S™ Aluminum oxide(59%), Amorphous silica, Heavy mineral spirits, Titanium dioxide(23.0%), Weather resistant mixture **GAL WT: 23.31 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 64.52 SOLVENT DENSITY: 6.50 VOC LE: 2.3 VOC AP: 2.3 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1021S™ Aluminum oxide(47%), Amorphous silica, Heavy mineral spirits, Titanium dioxide(35.1%), Weather resistant mixture **GAL WT: 24.15 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 60.80 SOLVENT DENSITY: 6.50 VOC LE: 2.4 VOC AP: 2.4 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1023S™ Aluminum oxide(44%), Amorphous silica, Heavy mineral spirits, Iron oxide, Weather resistant mixture **GAL WT: 24.15 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 62.83 SOLVENT DENSITY: 6.50 VOC LE: 2.4 VOC AP: 2.4 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1024S™ Aluminum oxide(39%), Amorphous silica, Heavy mineral spirits, Tin oxide, Titanium dioxide(41.0%), Weather resistant mixture **GAL WT: 18.33 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 76.14 SOLVENT DENSITY: 6.50 VOC LE: 1.8 VOC AP: 1.8 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1025S™ Aluminum oxide(32%), Amorphous silica, Heavy mineral spirits, Titanium dioxide(52.1%), Weather resistant mixture **GAL WT: 22.53 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 72.20 SOLVENT DENSITY: 6.50 VOC LE: 2.3 VOC AP: 2.3 FLASH POINT: Above 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1026S™ Iron oxide, Mica, Polyoxyalkylenes, Titanium dioxide (rutile)(27.8%) **GAL WT: 26.20 WT PCT SOLIDS: 100.00 VOL PCT SOLIDS: 100.00 SOLVENT DENSITY: 0.00 VOC LE: 0.0 VOC AP: 0.0 FLASH POINT: Above 200 °F H: 1 F: R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

801J™ , Aluminum hydroxide, Amorphous silica, Butyl acetate, Ethylbenzene(3.9%***@**), Titanium dioxide(49.2%), Xylene(15%***@**) **GAL WT: 13.50 WT PCT SOLIDS: 73.51 VOL PCT SOLIDS: 50.70 SOLVENT DENSITY: 7.25 VOC LE: 3.9 VOC AP: 3.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

802J™ , Butyl acetate, Ethylbenzene(6.4%***@**), Methyl methacrylate(1%***@**), Titanium dioxide(4.7%), Xylene(26%***@**) **GAL WT: 8.50 WT PCT SOLIDS: 54.52 VOL PCT SOLIDS: 46.73 SOLVENT DENSITY: 7.26 VOC LE: 3.9 VOC AP: 3.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

803J™ , Aluminum oxide(3%*), Butyl acetate, Ethylbenzene(5.8%***@**), Titanium dioxide(33.6%), Xylene(23%***@**) **GAL WT: 11.07 WT PCT SOLIDS: 60.27 VOL PCT SOLIDS: 39.38 SOLVENT DENSITY: 7.25 VOC LE: 4.4 VOC AP: 4.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

805J™ , Butyl acetate, Carbon black(4.5%), Ethylbenzene(7.0%***@**), Xylene(28%***@**) **GAL WT: 8.27 WT PCT SOLIDS: 50.33 VOL PCT SOLIDS: 43.42 SOLVENT DENSITY: 7.25 VOC LE: 4.1 VOC AP: 4.1 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

806J™ , Aluminum benzoate, Butyl acetate, Carbon black(2.9%), Ethylbenzene(7.3%***@**), Xylene(29%***@**) **GAL WT: 8.23 WT PCT SOLIDS: 48.47 VOL PCT SOLIDS: 41.58 SOLVENT DENSITY: 7.25 VOC LE: 4.2 VOC AP: 4.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

807J™ , Butyl acetate, Carbon black(0.3%), Ethylbenzene(7.1%***@**), Xylene(28%***@**) **GAL WT: 8.14 WT PCT SOLIDS: 49.44 VOL PCT SOLIDS: 43.32 SOLVENT DENSITY: 7.25 VOC LE: 4.1 VOC AP: 4.1 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

808J™ , Butyl acetate, Ethylbenzene(8.2%***@**), Graphite, Primary amyl acetate, Xylene(33%***@**) **GAL WT: 8.74 WT PCT SOLIDS: 44.29 VOL PCT SOLIDS: 32.87 SOLVENT DENSITY: 7.13 VOC LE: 4.9 VOC AP: 4.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

810J™ , 1,2,4-trimethyl benzene(1%*), Aluminum(15%*), Aromatic hydrocarbon-B, Butyl acetate, Ethylbenzene(6.7%***@**), Hydrotreated heavy naphtha (petroleum), Xylene(27%***@**) **GAL WT: 8.70 WT PCT SOLIDS: 47.17 VOL PCT SOLIDS: 35.91 SOLVENT DENSITY: 7.18 VOC LE: 4.6 VOC AP: 4.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

811J™ , 1,2,4-trimethyl benzene(1%*), Aluminum(26%*), Aromatic hydrocarbon-A, Aromatic hydrocarbon-B, Butyl acetate, Cumene(0.1%***@**), Ethylbenzene(5.7%***@**), Naphthalene(0.3%***@**), Stoddard solvent, Xylene(23%***@**) **GAL WT: 9.13 WT PCT SOLIDS: 47.99 VOL PCT SOLIDS: 35.08 SOLVENT DENSITY: 7.36 VOC LE: 4.7 VOC AP: 4.7 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

813J™ , 1,2,4-trimethyl benzene(2%*), Aluminum(19%*), Aromatic hydrocarbon-B, Butyl acetate, Cumene(0.1%***@**), Ethylbenzene(6.2%***@**), Stoddard solvent, Xylene(25%***@**) **GAL WT: 8.89 WT PCT SOLIDS: 47.71 VOL PCT SOLIDS: 34.48 SOLVENT DENSITY: 7.14 VOC LE: 4.6 VOC AP: 4.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

814J™ , 1,2,4-trimethyl benzene(2%*), Aluminum(23%*), Aromatic hydrocarbon-B, Butyl acetate, Ethylbenzene(6.6%***@**), Stoddard solvent, Xylene(26%***@**) **GAL WT: 9.14 WT PCT SOLIDS: 48.93 VOL PCT SOLIDS: 35.78 SOLVENT DENSITY: 7.35 VOC LE: 4.7 VOC AP: 4.7 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

815J™ , Aluminum(1%*), Butyl acetate, Calcined kaolin, Ethylbenzene(4.7%***@**), Xylene(19%***@**) **GAL WT: 10.96 WT PCT SOLIDS: 68.72 VOL PCT SOLIDS: 52.70 SOLVENT DENSITY: 7.24 VOC LE: 3.4 VOC AP: 3.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

816J™ , 1,2,4-trimethyl benzene(2%*), Aluminum(17%*), Aromatic hydrocarbon-B, Butyl acetate, Ethylbenzene(6.5%***@**), Stoddard solvent, Xylene(26%***@**) **GAL WT: 8.75 WT PCT SOLIDS: 45.57 VOL PCT SOLIDS: 34.04 SOLVENT DENSITY: 7.17 VOC LE: 4.8 VOC AP: 4.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

818J™ , Butyl acetate, Calcined kaolin, Ethylbenzene(4.5%***@**), Xylene(18%***@**) **GAL WT: 11.51 WT PCT SOLIDS: 70.83 VOL PCT SOLIDS: 53.74 SOLVENT DENSITY: 7.25 VOC LE: 3.4 VOC AP: 3.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

819J™ , 1,2,4-trimethyl benzene(2%*), Aluminum(21%*), Aromatic hydrocarbon-B, Butyl acetate, Ethylbenzene(6.6%***@**), Hydrotreated heavy naphtha (petroleum), Xylene(26%***@**) **GAL WT: 9.01 WT PCT SOLIDS: 47.35 VOL PCT SOLIDS: 34.66 SOLVENT DENSITY: 7.30 VOC LE: 4.7 VOC AP: 4.7 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

820J™ , Butyl acetate, Carbazole violet pigment, Ethylbenzene(9.1%***@**), Primary amyl acetate, Xylene(36%***@**) **GAL WT: 7.95 WT PCT SOLIDS: 35.50 VOL PCT SOLIDS: 29.29 SOLVENT DENSITY: 7.24 VOC LE: 5.1 VOC AP: 5.1 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

821J™ , Butyl acetate, C.i. pigment blue 60, Ethylbenzene(8.3%***@**), Primary amyl acetate, Xylene(33%***@**) **GAL WT: 8.08 WT PCT SOLIDS: 41.21 VOL PCT SOLIDS: 34.51 SOLVENT DENSITY: 7.25 VOC LE: 4.8 VOC AP: 4.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

Compliance PHOTOCHEMICALLY REACTIVE: YES

826J™ , Butyl acetate, Ethylbenzene(9.6%*), Phthalocyanine blue pigment, Primary amyl acetate, Xylene(38%*) **GAL WT: 7.96 WT PCT SOLIDS: 32.16 VOL PCT SOLIDS: 25.54 SOLVENT DENSITY: 7.25 VOC LE: 5.4 VOC AP: 5.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

827J™ , Butyl acetate, Ethylbenzene(10.0%*), Phthalocyanine blue, Primary amyl acetate, Xylene(40%*) **GAL WT: 7.95 WT PCT SOLIDS: 29.69 VOL PCT SOLIDS: 22.95 SOLVENT DENSITY: 7.25 VOC LE: 5.6 VOC AP: 5.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

828J™ , Butyl acetate, Ethylbenzene(9.0%*), Phthalocyanine blue pigment, Primary amyl acetate, Xylene(36%*) **GAL WT: 8.12 WT PCT SOLIDS: 36.28 VOL PCT SOLIDS: 28.68 SOLVENT DENSITY: 7.25 VOC LE: 5.2 VOC AP: 5.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

829J™ , Butyl acetate, Ethylbenzene(7.5%*), Phthalocyanine blue pigment, Proprietary copper compound(1%*), Xylene(30%*) **GAL WT: 8.36 WT PCT SOLIDS: 46.84 VOL PCT SOLIDS: 38.74 SOLVENT DENSITY: 7.25 VOC LE: 4.4 VOC AP: 4.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

830J™ , Butyl acetate, Ethylbenzene(8.7%*), Phthalocyanine green, Primary amyl acetate, Xylene(35%*) **GAL WT: 8.26 WT PCT SOLIDS: 38.53 VOL PCT SOLIDS: 29.99 SOLVENT DENSITY: 7.25 VOC LE: 5.1 VOC AP: 5.1 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

831J™ , Butyl acetate, Ethylbenzene(6.9%*), Phthalocyanine green, Xylene(27%*) **GAL WT: 8.23 WT PCT SOLIDS: 51.10 VOL PCT SOLIDS: 44.57 SOLVENT DENSITY: 7.26 VOC LE: 4.0 VOC AP: 4.0 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

832J™ , Butyl acetate, Ethylbenzene(7.8%*), Phthalocyanine green pigment, Primary amyl acetate, Xylene(31%*) **GAL WT: 8.56 WT PCT SOLIDS: 44.78 VOL PCT SOLIDS: 34.91 SOLVENT DENSITY: 7.25 VOC LE: 4.7 VOC AP: 4.7 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

833J™ , Azomethine copper-complex(7%*), Butyl acetate, Ethylbenzene(9.2%*), Primary amyl acetate, Xylene(37%*) **GAL WT: 7.98 WT PCT SOLIDS: 34.85 VOL PCT SOLIDS: 28.33 SOLVENT DENSITY: 7.25 VOC LE: 5.2 VOC AP: 5.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

841J™ , Butyl acetate, Ethylbenzene(7.4%*), Isoindolinone yellow pigment, Primary amyl acetate, Xylene(29%*) **GAL WT: 8.58 WT PCT SOLIDS: 47.99 VOL PCT SOLIDS: 38.49 SOLVENT DENSITY: 7.25 VOC LE: 4.5 VOC AP: 4.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

843J™ , Butyl acetate, C.i. pigment yellow 154, Ethylbenzene(7.6%*), Primary amyl acetate, Xylene(30%*) **GAL WT: 8.45 WT PCT SOLIDS: 46.54 VOL PCT SOLIDS: 37.68 SOLVENT DENSITY: 7.24 VOC LE: 4.5 VOC AP: 4.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

845J™ , 2-methyl butyl acetate, Butyl acetate, Ethylbenzene(10.4%*), Primary amyl acetate, Tetrachloroisosolinone yellow pigment, Xylene(41%*) **GAL WT: 7.89 WT PCT SOLIDS: 27.09 VOL PCT SOLIDS: 20.67 SOLVENT DENSITY: 7.25 VOC LE: 5.8 VOC AP: 5.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

846J™ , Butyl acetate, Ethylbenzene(7.2%*), Isoindolinone pigment, Primary amyl acetate, Xylene(29%*) **GAL WT: 8.65 WT PCT SOLIDS: 49.38 VOL PCT SOLIDS: 39.66 SOLVENT DENSITY: 7.25 VOC LE: 4.4 VOC AP: 4.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

850J™ , Butyl acetate, C.i. pigment red 254, Ethylbenzene(7.5%*), Primary amyl acetate, Xylene(30%*) **GAL WT: 8.45 WT PCT SOLIDS: 47.21 VOL PCT SOLIDS: 38.51 SOLVENT DENSITY: 7.25 VOC LE: 4.5 VOC AP: 4.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

853J™ , Butyl acetate, Ethylbenzene(7.4%*), Monoazo pigment, Primary amyl acetate, Xylene(29%*) **GAL WT: 8.59 WT PCT SOLIDS: 48.04 VOL PCT SOLIDS: 38.47 SOLVENT DENSITY: 7.26 VOC LE: 4.5 VOC AP: 4.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

855J™ , Butyl acetate, Ethylbenzene(8.6%*), Perylene pigment, Primary amyl acetate, Xylene(34%*) **GAL WT: 8.16 WT PCT SOLIDS: 39.16 VOL PCT SOLIDS: 31.60 SOLVENT DENSITY: 7.25 VOC LE: 5.0 VOC AP: 5.0 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

858J™ , Butyl acetate, Ethylbenzene(7.2%*), Perylene pigment, Xylene(29%*) **GAL WT: 8.29 WT PCT SOLIDS: 48.71 VOL PCT SOLIDS: 41.37 SOLVENT DENSITY: 7.25 VOC LE: 4.3 VOC AP: 4.3 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

861J™ , Butyl acetate, C.i. pigment red 254, Ethylbenzene(8.7%*), Pigment red 202, Primary amyl acetate, Substituted pyrrolpyrrol, Xylene(34%*) **GAL WT: 8.07 WT PCT SOLIDS: 38.95 VOL PCT SOLIDS: 32.07 SOLVENT DENSITY: 7.24 VOC LE: 4.9 VOC AP: 4.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

862J™, Butyl acetate, Ethylbenzene(8.6%*), Primary amyl acetate, Quinacridone magenta, Quinacridone pigment, Xylene(34%*) GAL WT: 8.04 WT PCT SOLIDS: 39.04 VOL PCT SOLIDS: 32.41 SOLVENT DENSITY: 7.24 VOC LE: 4.9 VOC AP: 4.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

864J™, Butyl acetate, Ethylbenzene(8.6%*), Pigment red 202, Primary amyl acetate, Quinacridone pigment, Xylene(34%*) GAL WT: 8.10 WT PCT SOLIDS: 39.23 VOL PCT SOLIDS: 32.12 SOLVENT DENSITY: 7.25 VOC LE: 4.9 VOC AP: 4.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

866J™, Butyl acetate, Ethylbenzene(7.4%*), Quinacridone pigment, Xylene(29%*) GAL WT: 8.33 WT PCT SOLIDS: 47.66 VOL PCT SOLIDS: 39.88 SOLVENT DENSITY: 7.25 VOC LE: 4.4 VOC AP: 4.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

870J™, Butyl acetate, Ethylbenzene(6.6%*), Methyl methacrylate(1%*), Xylene(26%*) GAL WT: 8.22 WT PCT SOLIDS: 53.04 VOL PCT SOLIDS: 46.81 SOLVENT DENSITY: 7.26 VOC LE: 3.9 VOC AP: 3.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

878J™, Aluminum(15%*), Butyl acetate, Ethylbenzene(5.7%*), Hydrotreated heavy naphtha (petroleum), Iron oxide, Xylene(23%*) GAL WT: 9.06 WT PCT SOLIDS: 52.91 VOL PCT SOLIDS: 39.46 SOLVENT DENSITY: 7.02 VOC LE: 4.3 VOC AP: 4.3 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

881J™, Butyl acetate, Ethylbenzene(5.3%*), Xylene(21%*), Yellow iron oxide GAL WT: 11.47 WT PCT SOLIDS: 63.44 VOL PCT SOLIDS: 42.22 SOLVENT DENSITY: 7.25 VOC LE: 4.2 VOC AP: 4.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

882J™, Butyl acetate, Ethylbenzene(6.4%*), Xylene(26%*), Yellow iron oxide GAL WT: 8.72 WT PCT SOLIDS: 54.74 VOL PCT SOLIDS: 45.61 SOLVENT DENSITY: 7.26 VOC LE: 3.9 VOC AP: 3.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

884J™, Butyl acetate, Ethylbenzene(6.4%*), Methyl methacrylate(1%*), Red iron oxide light, Xylene(25%*) GAL WT: 8.52 WT PCT SOLIDS: 54.58 VOL PCT SOLIDS: 46.72 SOLVENT DENSITY: 7.26 VOC LE: 3.9 VOC AP: 3.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

885J™, Acrylic polymer, Barium sulfate, Butyl acetate, Ethylbenzene(6.8%*), Perylene maroon, Propylene carbonate, Xylene(27%*) GAL WT: 8.58 WT PCT SOLIDS: 48.55 VOL PCT SOLIDS: 39.57 SOLVENT DENSITY: 7.30 VOC LE: 4.4 VOC AP: 4.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

886J™, Acrylic polymer, Butyl acetate, Ethylbenzene(6.7%*), Quinacridone pigment, Xylene(27%*) GAL WT: 8.48 WT PCT SOLIDS: 49.81 VOL PCT SOLIDS: 41.65 SOLVENT DENSITY: 7.29 VOC LE: 4.3 VOC AP: 4.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

890J™, Butyl acetate, Ethylbenzene(5.7%*), Light yellow lemon yellow oxide pigment, Xylene(23%*) GAL WT: 9.72 WT PCT SOLIDS: 59.74 VOL PCT SOLIDS: 46.11 SOLVENT DENSITY: 7.25 VOC LE: 3.9 VOC AP: 3.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

891J™, Butyl acetate, Ethylbenzene(6.3%*), Iron oxide, Xylene(25%*) GAL WT: 9.31 WT PCT SOLIDS: 55.04 VOL PCT SOLIDS: 42.31 SOLVENT DENSITY: 7.25 VOC LE: 4.2 VOC AP: 4.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

893J™, Butyl acetate, C.i. pigment brown, Ethylbenzene(9.3%*), Primary amyl acetate, Xylene(37%*) GAL WT: 8.00 WT PCT SOLIDS: 34.51 VOL PCT SOLIDS: 27.72 SOLVENT DENSITY: 7.24 VOC LE: 5.2 VOC AP: 5.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

894J™, Aluminum(25%*), Aromatic hydrocarbon-B, Butyl acetate, Ethylbenzene(6.8%*), Hydrotreated heavy naphtha (petroleum), Xylene(27%*) GAL WT: 9.08 WT PCT SOLIDS: 49.81 VOL PCT SOLIDS: 35.87 SOLVENT DENSITY: 7.04 VOC LE: 4.6 VOC AP: 4.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

895J™, 1,2,4-trimethyl benzene(2%*), Aluminum(22%*), Aromatic hydrocarbon-B, Butyl acetate, Ethylbenzene(6.1%*), Stoddard solvent, Xylene(24%*) GAL WT: 9.15 WT PCT SOLIDS: 51.45 VOL PCT SOLIDS: 38.46 SOLVENT DENSITY: 7.17 VOC LE: 4.4 VOC AP: 4.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

908J™, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(7.0%*), Mica, Polyethylene/vinyl acetate, Titanium dioxide(4.1%), Xylene(28%*) GAL WT: 8.31 WT PCT SOLIDS: 37.58 VOL PCT SOLIDS: 28.82 SOLVENT DENSITY: 7.28 VOC LE: 5.2 VOC AP: 5.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

913J™, Acetone, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(5.7%*), Heavy mineral spirits, Mica, Polyethylene/vinyl acetate, Titanium dioxide (rutile)(8.0%), Xylene(23%*) GAL WT: 8.75 WT PCT SOLIDS: 40.82 VOL PCT SOLIDS: 27.53 SOLVENT DENSITY: 7.14 VOC LE: 5.0 VOC AP: 4.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

915J™, Butyl acetate, Cellulose acetate butyrate, Ethylbenzene(6.9%*), Mica, Polyethylene/vinyl acetate, Titanium dioxide(3.8%), Xylene(28%*) GAL WT: 8.38 WT PCT SOLIDS: 38.29 VOL PCT SOLIDS: 28.99 SOLVENT DENSITY: 7.27 VOC LE: 5.2 VOC AP: 5.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

979J™, Aluminum(10%*), Butyl acetate, Ethylbenzene(5.7%*@), Hydrotreated heavy naphtha (petroleum), Iron oxide, Xylene(23%*@) **GAL WT: 9.10 WT PCT SOLIDS: 52.61 VOL PCT SOLIDS: 42.81 SOLVENT DENSITY: 7.02 VOC LE: 4.3 VOC AP: 4.3 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

Footnotes:

TSCA: in compliance In compliance with TSCA Inventory requirements for commercial purposes.

ACGIH American Conference of Governmental Industrial Hygienists.

IARC International Agency for Research on Cancer.

NTP National Toxicology Program.

OSHA Occupational Safety and Health Administration.

PNOR Particles not otherwise regulated.

PNOC Particles not otherwise classified.

STEL Short term exposure limit.

TWA Time-weighted average.

* VOC less exempt (theoretical) and VOC as packaged (theoretical) are based upon the VOC of the packaged material at the point of manufacture.

All products denoted with TM or ® are trademarks or registered trademarks of E. I. du Pont de Nemours and Company or its affiliates.

* = Section 313 Supplier Notification: These chemicals are subject to the reporting requirements of Section 313 of the Emergency planning and Right-to-Know act of 1986 and of 40 CFR 372.

@ = Listed as a Clean Air Act Hazardous Air Pollutant.

= EPCRA Section 302 - Extremely hazardous substances.

Notice:

The information on this Material Safety Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process.

Product Manager: Refinish Sales

Prepared by: Y. B. Yarbrough