

1. Identification of the substance/mixture and of the company/undertaking

Manufacturer: E. I. du Pont de Nemours and Company.
DuPont Performance Coatings
Wilmington, DE 19898

Telephone: Product information: (800) 441-7515
Medical emergency: (800) 441-3637
Transportation emergency: (800) 424-9300 (CHEMTREC)

Product: **Cromax® Pro**

DOT Shipping Name: See DOT Addendum.

Hazardous Materials Information: See Section 10.

Copyright 2011 E. I. du Pont de Nemours and Company. All rights reserved. Copies may be made only for those using DuPont products.

2. Composition/information on ingredients

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
2-amino-2-methyl-1-propanol	124-68-5	<0.3	D 500.0 ppm 8 & 12 hour TWA, A None, O None
Acetone	67-64-1	247.0@68.0 °F	A 750.0 ppm 15 min STEL, A 500.0 ppm, O 1000.0 ppm, D 500.0 ppm 8 & 12 hour TWA
Acrylic polymer-A	NotAvail	None	A None, O None
Acrylic polymer-B	146753-99-3	None	A None, O None
Acrylic polymer-C	70587-60-9	None	A None, O None
Acrylic resin	NotAvail	None	A None, O None
Acrylic resin (ts)	NotAvail	None	A None, O None
Acrylic resin - waterborne	NotAvail	None	A None, O None
Aliphatic polyisocyanate resin-A	NotAvail	27.0	A None, O None
Aliphatic polyisocyanate resin-B	28182-81-2	27.0	S 0.5 mg/m3, A None, O None
Aluminum	7429-90-5	None	O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, D 0.5 mg/m3 8 & 12 hour TWA, A None
Aluminum hydroxide	21645-51-2	None	A 1.0 mg/m3, O None
Aluminum oxide	1344-28-1	None	O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, A None
Amorphous silica	7631-86-9	None	A 3.0 mg/m3 Respirable Dust, O 20.0 mppcf, D 3.0 mg/m3, D 6.0 mg/m3
Azomethine copper-complex	15680-42-9	None	A None, O None
C.i. pigment blue 60	81-77-6	None	A None, O None
C.i. pigment brown	6992-11-6	None	A None, O None
C.i. pigment red 254	84632-65-5	None	A None, O None
C.i. pigment yellow 138	30125-47-4	None	A None, O None
Carbazole violet pigment	6358-30-1	None	A None, O None
Carbon black	1333-86-4	None	A 3.0 mg/m3, O 3.5 mg/m3, D 0.5 mg/m3 8 & 12 hour TWA
Carbon black, hydroxy & 4-sulfophenyl-modified, sod	481066-70-0	None	A 3.5 mg/m3, O 3.5 mg/m3, D 0.5 mg/m3 8 & 12 hour TWA
Copper phthalocyanine	147-14-8	None	A None, O None
Diketo-pyrrolopyrrol red pigment	88949-33-1	None	A 3.0 mg/m3 Respirable Dust, A 10.0 mg/m3, O 15.0 mg/m3, O 5.0 mg/m3 TWA Respirable Dust
Dipropylene glycol methyl ether	34590-94-8	0.4@25.0 °C	A None, O None
Dispersing agent	35545-57-4	<0.0	A None, O None
Ethanol, 2-(2-butoxyethoxy)-	112-34-5	0.0	D 5.0 ppm, A None, O None
Ethylene glycol monobutyl ether	111-76-2	0.6	A 20.0 ppm, O 50.0 ppm Skin, D 20.0 ppm 8 & 12 hour TWA
Hydrotreated heavy naphtha (petroleum)	64742-48-9	0.7@68.0 °F	A 100.0 ppm, O 500.0 ppm, D 100.0 ppm
Hydroxyfunctional acrylic resin	NotAvail	None	A None, O None
Iron hydroxide	20344-49-4	None	A None, O None
Iron oxide	1309-37-1	None	A 5.0 mg/m3 Respirable Dust, O 10.0 mg/m3, D 3.0 mg/m3
Isoindolinone pigment	36888-99-0	None	A None, O None
Isopropyl alcohol	67-63-0	48.0	A None, O None
Light yellow lemon yellow oxide pigment	51274-00-1	None	A None, O None
Mica	12001-26-2	None	A 3.0 mg/m3 Respirable Dust, O 20.0 mppcf, O 3.0 mg/m3 Respirable Dust
Monoazo pigment	12236-62-3	None	A 10.0 mg/m3 inhalable dust particulate, O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
N,n-dimethylethanolamine	108-01-0	4.4	D 2.0 ppm 8 & 12 hour TWA, A None, O None
N-pentanol	71-41-0	1.5	A None, O None
N-propanol	71-23-8	19.0	A 100.0 ppm, O 250.0 ppm 15 min STEL, O 200.0 ppm Skin, D 200.0 ppm
Perylene pigment	5521-31-3	None	A 10.0 mg/m3, O None
Phthalocyanine blue pigment	147-14-8	None	A 10.0 mg/m3 inhalable dust PNOC, A 3.0 mg/m3 respirable particulate PNOC, O 15.0 mg/m3 Total Dust PNOR, O 5.0 mg/m3 TWA Respirable Dust PNOR
Phthalocyanine green	1328-53-6	None	A 3.0 mg/m3 TWA Respirable Dust, A 10.0 mg/m3 TWA inhalable dust, O 15.0 mg/m3 TWA Total Dust, O 5.0 mg/m3 TWA Respirable Dust
Phthalocyanine green pigment	14302-13-7	None	A None, O None
Pigment red 202	3089-17-6	None	A 3.0 mg/m3 Respirable Dust, A 10.0 mg/m3 inhalable dust PNOR, O 5.0 mg/m3 Respirable Dust PNOR, O 15.0 mg/m3
Polyether modified siloxane	NotAvail	<1.0	A None, O None
Polypropylene glycol	25322-69-4	<0.0	A None, O None
Polyurethane resin-A	NotAvail	None	A None, O None
Polyurethane resin-B	.	None	A None, O None
Propanol, 1(or 2)-ethoxy-	1569-02-4	10.0	A None, O None
Proprietary copper compound	NotAvail	None	A None, O None
Propylene glycol methyl ether	107-98-2	11.2@77.0 ° F	A 150.0 ppm 15 min STEL, A 100.0 ppm, O None
Propylene glycol monomethyl ether acetate	108-65-6	3.8	D 30.0 ppm 15 min TWA, A None, O None
Quinacridone pigment	1047-16-1	None	A 10.0 mg/m3 inhalable dust, A 3.0 mg/m3, O 15.0 mg/m3 Total Dust PNOR, O 5.0 mg/m3 Respirable Dust, D 10.0 mg/m3 Total Dust
Rheology agent	NotAvail	18.0	A None, O None
Synthetic magnesium silicate	53320-86-8	None	S 15.0 mg/m3 PNOR Total Dust, S 5.0 mg/m3 PNOR Respirable Dust, A 3.0 mg/m3 Respirable Dust, O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust
Tetrachloroisosolinone yellow pigment	5590-18-1	None	A 250.0 ppm, O None
Titanium dioxide	13463-67-7	None	O 15.0 mg/m3 Total Dust, D 10.0 mg/m3 Total Dust, D 5.0 mg/m3 Respirable Dust, A None
Titanium dioxide (rutile)	1317-80-2	None	A 10.0 mg/m3 TWA Total Dust, O 10.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, D 10.0 mg/m3 Total Dust, D 5.0 mg/m3 Respirable Dust
Urea-formaldehyde condensation polymer	9011-05-6	None	A None, O None
Water	7732-18-5	23.6	A None, O None
Yellow pigment	NotAvail	None	A None, O None

*A=ACGIH, O=OSHA, D=DuPont, S=Suppliers. Limits are 8 hour TWA unless otherwise specified. Vapor pressure @ 20° C unless otherwise noted.

3. Hazards identification

Potential Health Effects:

Inhalation:

May cause nose and throat irritation. May cause nervous system depression, characterized by the following progressive steps: headache, dizziness, nausea, staggering gait, confusion, unconsciousness. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. If this product contains or is mixed with an isocyanate activator/hardener, the following health effects may apply: Exposure to isocyanates may cause respiratory sensitization. This effect may be permanent. Symptoms include an asthma-like reaction with shortness of breath, wheezing, cough or permanent lung sensitization. This effect may be delayed for several hours after exposure. Repeated overexposure to isocyanates may cause a decrease in lung function, which may be permanent. Individuals with lung or breathing problems or prior reactions to isocyanates must not be exposed to vapors or spray mist of this product.

Ingestion:

May result in gastrointestinal distress.

Skin or eye contact:

May cause irritation or burning of the eyes. Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis.

Other Potential Health Effects in addition to those listed above:

2-amino-2-methyl-1-propanol

Eye burns. Ingestion may cause any of the following: burns to mouth and stomach, gastrointestinal irritation, aspiration leading to lung damage..

Acetone

The following medical conditions may be aggravated by exposure: lung disease, eye disorders, skin disorders. Overexposure may cause damage to any of the following organs/systems: blood, central nervous system, eyes, kidneys, liver, respiratory system, skin.

Acrylic resin (ts)

Skin or eye contact may cause any of the following: irritation.

Aliphatic polyisocyanate resin-B

Overexposure may cause asthma-like reactions with shortness of breath, wheezing, cough, which may be permanent; or permanent lung sensitization. This effect may be delayed for several hours after exposure. The following medical conditions may be aggravated by exposure: asthma, skin disorders, respiratory disorders. Potential skin sensitizer that may cause allergic reactions and contact dermatitis resulting in severe irritation, dryness, and cracking of the skin.

Carbon black

Is an IARC, NTP or OSHA carcinogen. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. The following medical conditions may be aggravated by exposure: asthma, respiratory disease. WARNING: This chemical is known to the State of California to cause cancer.

Ethanol, 2-(2-butoxyethoxy)-

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, eyes, kidneys, liver, skin. Tests in laboratory animals have shown effects on any of the following organs/systems: blood, kidneys, liver. Recurrent overexposure may result in liver and kidney injury. High doses in laboratory animals have shown non specific effects such as irritation, weight loss, moderate blood changes. Eye contact may cause any of the following: severe irritation, burns, corneal injury.

Ethylene glycol monobutyl ether

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow, central nervous system, eyes, gastrointestinal system, kidneys, liver, respiratory system, skin. May cause injury to the kidneys, liver, blood and/or bone marrow. Repeated overexposure may result in damage to the blood. Eye contact may cause corneal injury. If absorbed through the skin, may be: harmful.

Hydrotreated heavy naphtha (petroleum)

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Isopropyl alcohol

The following medical conditions may be aggravated by exposure: dermatitis, respiratory disease. Developmental toxicity was seen in rat's offspring at doses that were maternally toxic. Contact may cause skin irritation with discomfort or rash. Can be absorbed through the skin in harmful amounts. Contact will cause moderate to severe redness and swelling, itching, tingling sensation, painful burning. May cause injury to the cornea of the eyes. Prolonged or repeated exposure may cause damage to any of the following organs/systems: liver. Ingestion studies on laboratory animals showed that very high oral doses caused increased liver and kidney weights. Aspiration may occur during swallowing or vomiting, resulting in lung damage. May cause central nervous system depression with headache, stupor, uncoordinated or strange behavior, or unconsciousness. Irritating to the mouth, throat and stomach. May cause irritation of the respiratory tract, experienced as nasal discomfort and discharge, coughing and possibly accompanied by chest pain. Prolonged or repeated skin contact may cause drying, cracking, or irritation. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness. Swallowing significant amounts of substance could cause serious injury, even death.

Light yellow lemon yellow oxide pigment

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

Mica

Repeated or prolonged inhalation may cause any of the following: lung irritation. Long-term respiratory exposure exceeding TLV may damage the lungs, leading to bronchitis and impairment of lung capacity.

N-propanol

Has shown mutagenic activity in laboratory cell culture tests. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. May cause abnormal liver function. Can be absorbed through the skin in harmful amounts.

Polyether modified siloxane

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

Propylene glycol methyl ether

Tests in laboratory animals have shown effects on any of the following organs/systems: kidneys, liver. Aspiration may occur during swallowing or vomiting, resulting in lung damage.

Propylene glycol monomethyl ether acetate

Recurrent overexposure may result in liver and kidney injury.

Titanium dioxide

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m3 respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m3 level are not relevant to the workplace. Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium Dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.'

Titanium dioxide (rutile)

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m3 respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m3 level are not relevant to the workplace. Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.'

Urea-formaldehyde condensation polymer

This chemical is a formaldehyde donor. Formaldehyde is an IARC, NTP or OSHA carcinogen and has shown mutagenic activity in laboratory cell culture tests. May induce pulmonary sensitization or significant irritation of the respiratory airways. Formaldehyde has produced tumors in the nasal passages of laboratory animals when exposed to high concentrations for a two year period. IARC has concluded epidemiology studies found evidence of formaldehyde related nasopharyngeal cancer in humans and have classified formaldehyde as a confirmed human carcinogen. DuPont toxicologists have reviewed these studies and classified formaldehyde as a possible human carcinogen.

4. First aid measures

First Aid Procedures:

Inhalation:

If affected by inhalation of vapor or spray mist, move to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. If breathing difficulty persists, or occurs later, consult a physician.

Ingestion:

In the unlikely event of ingestion, DO NOT INDUCE VOMITING. Call a physician immediately and have names of ingredients available.

Skin or eye contact:

In case of eye contact, immediately flush with plenty of water for at least 15 minutes; call a physician. In case of skin contact, wash thoroughly with soap and water. If irritation occurs, contact a physician.

5. Fire-fighting measures

Flash Point (Closed Cup):

See Section 11 for exact values.

Flammable Limits: LFL 1.1 % UFL 14 %

Extinguishing Media:

Universal aqueous film-forming foam, carbon dioxide, dry chemical.

Fire Fighting Procedures:

Full protective equipment, including self-contained breathing apparatus, is recommended. Water from fog nozzles may be used to prevent pressure build-up.

Fire and Explosion Hazards:

For flammable liquids, vapor/air will ignite when an ignition source is present. In other cases, when heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

6. Accidental release measures

Procedures for cleaning up spills or leaks:

Ventilate area. Remove sources of ignition. Prevent skin and eye contact and breathing of vapor. If material does not contain or is not mixed with an isocyanate activator/hardener: Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C), eye protection, gloves and protective clothing. Confine, remove with inert absorbent, and dispose of properly. If the material contains, or is mixed with an isocyanate activator/hardener: Wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C), eye protection, gloves and protective clothing. Pour liquid decontamination solution over the spill and allow to sit at least 10 minutes. Typical decontamination solutions for isocyanate containing materials are: 20% Surfactant (Tergitol TMN 10) and 80% Water OR 0-10% Ammonia, 2-5% Detergent and Water (balance). Pressure can be generated. Do not seal waste containers for 48 hours to allow CO₂ to vent. After 48 hours, material may be sealed and disposed of properly.

Ecological information:

There is no data available on the product. The product should not be allowed to enter drains, water courses or the soil.

7. Handling and storage

Precautions to be taken in handling and storing:

Observe label precautions. If combustible (flashpoint between 38-93 deg C or 100 - 200 deg F), keep away from heat, sparks and flame. If flammable (flashpoint less than 38 deg C or 100 deg F), also keep away from static discharges and other sources of ignition. If material is extremely flammable (flashpoint less than - 8 deg C or 20 deg F) or flammable, VAPORS MAY IGNITE EXPLOSIVELY OR CAUSE FLASH FIRE, respectively. Vapors may spread long distances. Prevent buildup of vapors. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 49 deg C or 120 deg F. If product is waterbased, do not freeze.

Other precautions:

If material is a coating: do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves. Combustible dust clouds may be created where operations produce fine material (dust). Avoid formation of significant deposits of material as they may become airborne and form combustible dust clouds. Handling and processing operations should be conducted in accordance with best practices (e.g.NFPA-654).

8. Exposure controls/personal protection

Ventilation:

Provide sufficient ventilation in volume and pattern to keep contaminants below applicable exposure limits.

Respiratory protection:

Do not breathe vapors or mists. If this product contains isocyanates or is used with an isocyanate activator/hardener, wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C) while mixing activator/hardener with paint, during application and until all vapors and spray mist are exhausted. If product does not contain or is not mixed with an isocyanate activator/hardener, a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH TC-23C) and particulate filter (NIOSH

TC-84A) may be used. Follow respirator manufacturer's directions for respirator use. Do not permit anyone without protection in the painting area. Individuals with history of lung or breathing problems or prior reaction to isocyanates should not use or be exposed vapor or spray mist if product contains or is mixed with isocyanate activators/hardeners.

Protective equipment:

Personal protective equipment should be worn to prevent contact with eyes, skin or clothing.

Skin and body protection:

Neoprene gloves and coveralls are recommended.

Desirable in all industrial situations. Goggles are preferred to prevent eye irritation. If safety glasses are substituted, include splash guard or side shields.

9. Physical and chemical properties

Evaporation rate	Slower than Ether
Water solubility	NIL
Vapour density	Heavier than air
Approx. Boiling Range (°C)	82 – 190 °C
Approx. Freezing Range (°C)	-127 – -95 °C
Gallon Weight (lbs/gal)	7.93648 - 13.7282
Specific Gravity	0.95 - 1.65
Percent Volatile By Volume	34.11 - 100.00
Percent Volatile By Weight	0.32 - 100.00
Percent Solids By Volume	0.00 - 65.90
Percent Solids By Weight	0.00 - 70.00

10. Stability and reactivity**Stability:**

Stable

Incompatibility (materials to avoid):

None reasonably foreseeable

Hazardous decomposition products:

CO, CO₂, smoke, and oxides of any heavy metals that are reported in "Composition, Information on Ingredients" section.

Hazardous Polymerization:

Will not occur.

Sensitivity to Static Discharge:

For flammable materials (flashpoint less than 38 deg C or 100 deg F) and combustibles (flashpoint between 38- 93 deg C or 100-200 deg F) if heated above the flashpoint, solvent vapors in air may explode if static grounding and bonding is not used during transfer of this product.

Sensitivity to Mechanical Impact:

None known.

11. Additional Information

HT800™ Ethanol, 2-(2-butoxyethoxy)-(2%*@), Hydroxyfunctional acrylic resin, N,n-dimethylethanolamine, Polyether modified siloxane, Propanol, 1(or 2)-ethoxy-, Water
GAL WT: 8.69 WT PCT SOLIDS: 44.44 VOL PCT SOLIDS: 40.02 SOLVENT DENSITY: 8.21 VOC LE: 1.4 VOC AP: 0.7 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0
OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

WB01™ Acrylic polymer-C, Acrylic resin (ts), Aluminum hydroxide, Amorphous silica, Dipropylene glycol methyl ether, Polyurethane resin-A, Titanium dioxide(48.9%), Water
GAL WT: 13.73 WT PCT SOLIDS: 58.47 VOL PCT SOLIDS: 30.99 SOLVENT DENSITY: 8.22 VOC LE: 1.7 VOC AP: 0.7 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0
OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

WB02™ Acrylic resin - waterborne, N-pentanol, Polyurethane resin-B, Titanium dioxide(6.8%), Water
GAL WT: 8.87 WT PCT SOLIDS: 21.09 VOL PCT SOLIDS: 15.19 SOLVENT DENSITY: 8.25 VOC LE: 2.1 VOC AP: 0.5 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0
OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

WB03™ Acrylic polymer-C, Acrylic resin (ts), Aluminum hydroxide, Dipropylene glycol methyl ether, Isopropyl alcohol, Titanium dioxide(17.9%), Water
GAL WT: 9.67 WT PCT SOLIDS: 25.13 VOL PCT SOLIDS: 12.35 SOLVENT DENSITY: 8.26 VOC LE: 3.4 VOC AP: 0.8 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0
OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

WB05™ Acrylic polymer-B, Carbon black(3.5%), Water
GAL WT: 8.54 WT PCT SOLIDS: 16.14 VOL PCT SOLIDS: 13.84 SOLVENT DENSITY: 8.31 VOC LE: 0.1 VOC AP: 0.0 FLASH POINT: Above 200 °F H: 1 F: 1 R: 0
OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

WB06™ Carbon black(1.8%), Dispersing agent, Water
GAL WT: 8.44 WT PCT SOLIDS: 6.12 VOL PCT SOLIDS: 4.73 SOLVENT DENSITY: 8.32 VOC LE: 1.4 VOC AP: 0.1 FLASH POINT: 141 °F - 200 °F H: 0 F: 2 R: 0
OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

WB07™ Acrylic resin - waterborne, Carbon black(0.6%), N-pentanol, Polyurethane resin-B, Water
GAL WT: 8.40 WT PCT SOLIDS: 11.93 VOL PCT SOLIDS: 10.56 SOLVENT DENSITY: 8.24 VOC LE: 2.2 VOC AP: 0.3 FLASH POINT: 141 °F - 200 °F H: 0 F: 2 R: 0
OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

WB1001™ Acrylic resin, Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide (rutile)(2.2%), Water **GAL WT: 8.77 WT PCT SOLIDS: 26.12 VOL PCT SOLIDS: 20.14 SOLVENT DENSITY: 8.11 VOC LE: 3.1 VOC AP: 1.1 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1002™ Acrylic resin, Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide (rutile)(3.4%), Water **GAL WT: 8.81 WT PCT SOLIDS: 27.19 VOL PCT SOLIDS: 20.87 SOLVENT DENSITY: 8.10 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1003™ Acrylic resin, Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide(3.8%), Water **GAL WT: 8.80 WT PCT SOLIDS: 26.52 VOL PCT SOLIDS: 20.30 SOLVENT DENSITY: 8.11 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1004™ Acrylic resin, Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide(4.8%), Water **GAL WT: 8.84 WT PCT SOLIDS: 27.55 VOL PCT SOLIDS: 21.04 SOLVENT DENSITY: 8.11 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1005™ Acrylic resin, Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide (rutile)(3.8%), Water **GAL WT: 8.79 WT PCT SOLIDS: 25.69 VOL PCT SOLIDS: 19.62 SOLVENT DENSITY: 8.12 VOC LE: 3.1 VOC AP: 1.1 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1006™ Acrylic resin, Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide(3.6%), Water **GAL WT: 8.81 WT PCT SOLIDS: 26.85 VOL PCT SOLIDS: 20.55 SOLVENT DENSITY: 8.11 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1007™ Acrylic resin, Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide (rutile)(4.4%), Water **GAL WT: 8.83 WT PCT SOLIDS: 27.34 VOL PCT SOLIDS: 20.88 SOLVENT DENSITY: 8.11 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1008™ Acrylic resin, Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide(5.5%), Water **GAL WT: 8.86 WT PCT SOLIDS: 28.15 VOL PCT SOLIDS: 21.46 SOLVENT DENSITY: 8.10 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1009™ Acrylic resin, Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide(3.3%), Water **GAL WT: 8.82 WT PCT SOLIDS: 27.77 VOL PCT SOLIDS: 21.39 SOLVENT DENSITY: 8.10 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1011™ Acrylic resin, Acrylic resin - waterborne, Iron oxide, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Water **GAL WT: 8.83 WT PCT SOLIDS: 27.55 VOL PCT SOLIDS: 21.11 SOLVENT DENSITY: 8.11 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1012™ Acrylic resin, Acrylic resin - waterborne, Iron oxide, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Water **GAL WT: 8.83 WT PCT SOLIDS: 27.59 VOL PCT SOLIDS: 21.14 SOLVENT DENSITY: 8.10 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1013™ Acrylic resin, Acrylic resin - waterborne, Iron oxide, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Water **GAL WT: 8.86 WT PCT SOLIDS: 28.16 VOL PCT SOLIDS: 21.39 SOLVENT DENSITY: 8.09 VOC LE: 3.2 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1014™ Acrylic resin, Acrylic resin - waterborne, Mica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide(4.7%), Water **GAL WT: 8.83 WT PCT SOLIDS: 27.45 VOL PCT SOLIDS: 20.98 SOLVENT DENSITY: 8.10 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1020™ Acrylic resin, Acrylic resin - waterborne, Aluminum oxide(6%), N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide(2.0%), Water **GAL WT: 8.87 WT PCT SOLIDS: 27.25 VOL PCT SOLIDS: 20.48 SOLVENT DENSITY: 8.11 VOC LE: 3.2 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1021™ Acrylic resin, Acrylic resin - waterborne, Aluminum oxide(4%), N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide (rutile)(3.7%), Water **GAL WT: 8.89 WT PCT SOLIDS: 28.99 VOL PCT SOLIDS: 21.94 SOLVENT DENSITY: 8.08 VOC LE: 3.2 VOC AP: 1.3 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1022™ Acrylic resin, Acrylic resin - waterborne, Aluminum oxide(3%), N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide(4.8%), Water **GAL WT: 8.88 WT PCT SOLIDS: 27.93 VOL PCT SOLIDS: 21.01 SOLVENT DENSITY: 8.10 VOC LE: 3.2 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1023™ Acrylic resin, Acrylic resin - waterborne, Aluminum oxide(4%), N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide(3.0%), Water **GAL WT: 8.85 WT PCT SOLIDS: 26.71 VOL PCT SOLIDS: 20.07 SOLVENT DENSITY: 8.11 VOC LE: 3.2 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1024™ Acrylic resin, Acrylic resin - waterborne, Aluminum oxide(4%), Iron oxide, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Water **GAL WT: 8.89 WT PCT SOLIDS: 27.61 VOL PCT SOLIDS: 20.65 SOLVENT DENSITY: 8.11 VOC LE: 3.2 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

WB1025™ Acrylic resin, Acrylic resin - waterborne, Aluminum oxide(5%*), Iron oxide, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Water **GAL WT: 8.90 WT PCT SOLIDS: 28.11 VOL PCT SOLIDS: 21.08 SOLVENT DENSITY: 8.12 VOC LE: 3.2 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1030™ Acrylic resin - waterborne, Aluminum(3%*), Ethylene glycol monobutyl ether(1%*), N-pentanol, N-propanol, Polyurethane resin-B, Propylene glycol methyl ether, Water **GAL WT: 8.52 WT PCT SOLIDS: 14.11 VOL PCT SOLIDS: 10.88 SOLVENT DENSITY: 8.22 VOC LE: 3.6 VOC AP: 0.8 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1031™ Acrylic resin, Acrylic resin - waterborne, Aluminum(6%*), Ethylene glycol monobutyl ether(1%*), Hydrotreated heavy naphtha (petroleum), Isopropyl alcohol, N-pentanol, N-propanol, Polyurethane resin-B, Propylene glycol methyl ether, Water **GAL WT: 8.50 WT PCT SOLIDS: 20.11 VOL PCT SOLIDS: 14.91 SOLVENT DENSITY: 7.97 VOC LE: 4.3 VOC AP: 1.6 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1032™ Acrylic resin, Acrylic resin - waterborne, Aluminum(6%*), Ethylene glycol monobutyl ether(1%*), Isopropyl alcohol, N-pentanol, N-propanol, Polyurethane resin-B, Propylene glycol methyl ether, Water **GAL WT: 8.53 WT PCT SOLIDS: 19.94 VOL PCT SOLIDS: 14.74 SOLVENT DENSITY: 8.01 VOC LE: 4.3 VOC AP: 1.6 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1033™ Acrylic resin, Acrylic resin - waterborne, Aluminum(5%*), Isopropyl alcohol, N-pentanol, N-propanol, Polyurethane resin-B, Propylene glycol methyl ether, Water **GAL WT: 8.59 WT PCT SOLIDS: 19.31 VOL PCT SOLIDS: 14.17 SOLVENT DENSITY: 8.12 VOC LE: 4.2 VOC AP: 1.6 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1035™ Acrylic resin, Acrylic resin - waterborne, Aluminum(6%*), Ethylene glycol monobutyl ether(1%*), N-pentanol, N-propanol, Polyurethane resin-B, Propylene glycol methyl ether, Water **GAL WT: 8.55 WT PCT SOLIDS: 22.18 VOL PCT SOLIDS: 16.84 SOLVENT DENSITY: 7.97 VOC LE: 3.9 VOC AP: 1.4 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1037™ Acrylic resin, Acrylic resin - waterborne, Aluminum(5%*), Isopropyl alcohol, N-pentanol, N-propanol, Polyurethane resin-B, Propylene glycol methyl ether, Water **GAL WT: 8.54 WT PCT SOLIDS: 21.35 VOL PCT SOLIDS: 16.45 SOLVENT DENSITY: 8.05 VOC LE: 3.8 VOC AP: 1.4 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1039™ Acrylic resin, Acrylic resin - waterborne, Aluminum(6%*), Ethylene glycol monobutyl ether(1%*), Hydrotreated heavy naphtha (petroleum), N-pentanol, N-propanol, Polyurethane resin-B, Propylene glycol methyl ether, Water **GAL WT: 8.61 WT PCT SOLIDS: 21.65 VOL PCT SOLIDS: 16.42 SOLVENT DENSITY: 8.07 VOC LE: 3.8 VOC AP: 1.3 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1041™ Acrylic resin, Acrylic resin - waterborne, Aluminum(7%*), N-pentanol, N-propanol, Polyurethane resin-B, Propylene glycol methyl ether, Water **GAL WT: 8.57 WT PCT SOLIDS: 21.85 VOL PCT SOLIDS: 16.45 SOLVENT DENSITY: 7.95 VOC LE: 3.7 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1050™ Acrylic resin (ts), Urea-formaldehyde condensation polymer, Water **GAL WT: 8.72 WT PCT SOLIDS: 17.05 VOL PCT SOLIDS: 13.33 SOLVENT DENSITY: 8.39 VOC LE: 0.8 VOC AP: 0.1 FLASH POINT: 141 °F - 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1078™ Acrylic resin, Acrylic resin - waterborne, Aluminum(4%*), Hydrotreated heavy naphtha (petroleum), Iron oxide, N-pentanol, N-propanol, Polyurethane resin-B, Propylene glycol methyl ether, Water **GAL WT: 8.44 WT PCT SOLIDS: 18.53 VOL PCT SOLIDS: 13.70 SOLVENT DENSITY: 7.96 VOC LE: 4.3 VOC AP: 1.6 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1725™ Acrylic resin, Acrylic resin - waterborne, Amorphous silica, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Titanium dioxide (rutile)(0.9%), Water **GAL WT: 8.76 WT PCT SOLIDS: 27.42 VOL PCT SOLIDS: 21.50 SOLVENT DENSITY: 8.02 VOC LE: 3.1 VOC AP: 1.2 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 0 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB1779™ Acrylic resin, Acrylic resin - waterborne, Aluminum(3%*), Hydrotreated heavy naphtha (petroleum), Iron oxide, N-pentanol, N-propanol, Polyurethane resin-A, Propylene glycol methyl ether, Water **GAL WT: 8.46 WT PCT SOLIDS: 18.40 VOL PCT SOLIDS: 14.49 SOLVENT DENSITY: 7.93 VOC LE: 4.4 VOC AP: 1.6 FLASH POINT: 100 °F - 141 °F H: 1 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB20™ Acrylic polymer-C, Acrylic resin (ts), Carbazole violet pigment, Dipropylene glycol methyl ether, Polyurethane resin-A, Water **GAL WT: 8.52 WT PCT SOLIDS: 11.27 VOL PCT SOLIDS: 8.94 SOLVENT DENSITY: 8.31 VOC LE: 2.1 VOC AP: 0.3 FLASH POINT: 141 °F - 200 °F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB2010™ Acetone, Acrylic resin - waterborne, N-pentanol, Polyurethane resin-B, Water **GAL WT: 8.46 WT PCT SOLIDS: 23.10 VOL PCT SOLIDS: 21.14 SOLVENT DENSITY: 8.25 VOC LE: 1.9 VOC AP: 0.5 FLASH POINT: 141 °F - 200 °F H: 2 F: 2 R: 1 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB2020™ Acrylic resin - waterborne, N-pentanol, Polyurethane resin-A, Water **GAL WT: 8.40 WT PCT SOLIDS: 14.34 VOL PCT SOLIDS: 13.02 SOLVENT DENSITY: 8.27 VOC LE: 1.9 VOC AP: 0.4 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB2030™ Acetone, Acrylic resin - waterborne, N-pentanol, Polyurethane resin-B, Water **GAL WT: 8.46 WT PCT SOLIDS: 23.31 VOL PCT SOLIDS: 21.33 SOLVENT DENSITY: 8.24 VOC LE: 1.9 VOC AP: 0.6 FLASH POINT: 141 °F - 200 °F H: 2 F: 2 R: 1 OSHA STORAGE: IIIA TSCA STATUS: In Compliance**

PHOTOCHEMICALLY REACTIVE: NO

WB2040™ Acrylic resin - waterborne, N-pentanol, Polypropylene glycol, Polyurethane resin-A, Synthetic magnesium silicate, Water **GAL WT: 8.40 WT PCT SOLIDS: 17.31 VOL PCT SOLIDS: 15.52 SOLVENT DENSITY: 8.22 VOC LE: 2.3 VOC AP: 0.5 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB2043™ Acrylic resin - waterborne, N-pentanol, Polypropylene glycol, Polyurethane resin-A, Synthetic magnesium silicate, Water **GAL WT: 8.40 WT PCT SOLIDS: 17.32 VOL PCT SOLIDS: 15.32 SOLVENT DENSITY: 8.20 VOC LE: 2.3 VOC AP: 0.5 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB2075™ Aliphatic polyisocyanate resin-A, Aliphatic polyisocyanate resin-B, Propylene glycol monomethyl ether acetate **GAL WT: 9.12 WT PCT SOLIDS: 70.00 VOL PCT SOLIDS: 65.90 SOLVENT DENSITY: 8.02 VOC LE: 2.7 VOC AP: 2.7 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB2091™ Acrylic resin - waterborne, N-pentanol, Polyurethane resin-A, Water **GAL WT: 8.42 WT PCT SOLIDS: 17.19 VOL PCT SOLIDS: 15.66 SOLVENT DENSITY: 8.26 VOC LE: 1.9 VOC AP: 0.4 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB2095™ Dipropylene glycol methyl ether **GAL WT: 7.94 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 7.94 VOC LE: 7.9 VOC AP: 7.9 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB21™ Acrylic polymer-C, Acrylic resin (ts), C.i. pigment blue 60, Isopropyl alcohol, Water **GAL WT: 8.77 WT PCT SOLIDS: 19.97 VOL PCT SOLIDS: 15.34 SOLVENT DENSITY: 8.29 VOC LE: 1.3 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB24™ Acrylic polymer-C, Acrylic resin (ts), Isopropyl alcohol, Phthalocyanine blue pigment, Water **GAL WT: 8.91 WT PCT SOLIDS: 22.80 VOL PCT SOLIDS: 17.06 SOLVENT DENSITY: 8.30 VOC LE: 1.3 VOC AP: 0.3 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB25™ Acrylic polymer-C, Acrylic resin (ts), Phthalocyanine blue pigment, Polyurethane resin-A, Water **GAL WT: 8.66 WT PCT SOLIDS: 13.26 VOL PCT SOLIDS: 9.60 SOLVENT DENSITY: 8.32 VOC LE: 1.4 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB26™ Acrylic resin - waterborne, N-pentanol, Polyurethane resin-B, Water **GAL WT: 8.42 WT PCT SOLIDS: 13.70 VOL PCT SOLIDS: 12.13 SOLVENT DENSITY: 8.22 VOC LE: 2.1 VOC AP: 0.4 FLASH POINT: 141 °F - 200 °F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB27™ Acrylic resin (ts), Dipropylene glycol methyl ether, Dispersing agent, Phthalocyanine blue pigment, Polyurethane resin-A, Water **GAL WT: 8.73 WT PCT SOLIDS: 16.96 VOL PCT SOLIDS: 12.71 SOLVENT DENSITY: 8.31 VOC LE: 2.5 VOC AP: 0.5 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB28™ Acrylic resin (ts), Copper phthalocyanine, Dipropylene glycol methyl ether, Dispersing agent, Polyurethane resin-A, Proprietary copper compound(2%*), Water **GAL WT: 8.93 WT PCT SOLIDS: 25.24 VOL PCT SOLIDS: 19.58 SOLVENT DENSITY: 8.30 VOC LE: 1.7 VOC AP: 0.4 FLASH POINT: 141 °F - 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB30™ Acrylic polymer-C, Phthalocyanine green, Polyurethane resin-A, Water **GAL WT: 8.91 WT PCT SOLIDS: 17.81 VOL PCT SOLIDS: 11.92 SOLVENT DENSITY: 8.31 VOC LE: 1.2 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB31™ Acrylic resin - waterborne, N-pentanol, Polyurethane resin-B, Water **GAL WT: 8.43 WT PCT SOLIDS: 13.45 VOL PCT SOLIDS: 11.76 SOLVENT DENSITY: 8.27 VOC LE: 2.1 VOC AP: 0.4 FLASH POINT: 141 °F - 200 °F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB32™ Acrylic polymer-C, Acrylic resin (ts), Dipropylene glycol methyl ether, Phthalocyanine green pigment, Polyurethane resin-A, Water **GAL WT: 9.46 WT PCT SOLIDS: 26.14 VOL PCT SOLIDS: 15.73 SOLVENT DENSITY: 8.30 VOC LE: 2.0 VOC AP: 0.4 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB40™ Acrylic polymer-C, Acrylic resin (ts), Azomethine copper-complex(9%*), Water **GAL WT: 8.67 WT PCT SOLIDS: 17.00 VOL PCT SOLIDS: 13.39 SOLVENT DENSITY: 8.31 VOC LE: 1.1 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB41™ Acrylic polymer-C, Acrylic resin (ts), C.i. pigment yellow 138, Dipropylene glycol methyl ether, Isopropyl alcohol, Water **GAL WT: 10.03 WT PCT SOLIDS: 40.49 VOL PCT SOLIDS: 27.82 SOLVENT DENSITY: 8.27 VOC LE: 1.3 VOC AP: 0.4 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB43™ Acrylic polymer-C, Acrylic resin (ts), Water, Yellow pigment **GAL WT: 9.23 WT PCT SOLIDS: 31.43 VOL PCT SOLIDS: 23.69 SOLVENT DENSITY: 8.32 VOC LE: 0.7 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

WB45™ Acrylic polymer-C, Polyurethane resin-A, Tetrachloroisosolinone yellow pigment, Water **GAL WT: 8.80 WT PCT SOLIDS: 16.77 VOL PCT SOLIDS: 11.89 SOLVENT DENSITY: 8.31 VOC LE: 1.0 VOC AP: 0.1 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance**

PHOTOCHEMICALLY REACTIVE: NO

WB46™ Dipropylene glycol methyl ether, Isoindolinone pigment, Polyurethane resin-A, Water **GAL WT: 9.18 WT PCT SOLIDS: 29.15 VOL PCT SOLIDS: 21.59**
SOLVENT DENSITY: 8.26 VOC LE: 1.8 VOC AP: 0.5 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

WB53™ Acrylic resin (ts), Dipropylene glycol methyl ether, Monoazo pigment, Water **GAL WT: 9.45 WT PCT SOLIDS: 34.04 VOL PCT SOLIDS: 24.91 SOLVENT**
DENSITY: 8.33 VOC LE: 0.9 VOC AP: 0.3 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

WB60™ Acrylic polymer-C, Acrylic resin (ts), C.i. pigment red 254, Dipropylene glycol methyl ether, Polyurethane resin-A, Water **GAL WT: 9.58 WT PCT SOLIDS: 39.59**
VOL PCT SOLIDS: 29.97 SOLVENT DENSITY: 8.27 VOC LE: 1.5 VOC AP: 0.5 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS:
In Compliance PHOTOCHEMICALLY REACTIVE: NO

WB61™ Acrylic polymer-C, Acrylic resin (ts), Diketo-pyrrolopyrrol red pigment, Polyurethane resin-A, Water **GAL WT: 8.55 WT PCT SOLIDS: 12.40 VOL PCT SOLIDS:**
9.87 SOLVENT DENSITY: 8.31 VOC LE: 1.2 VOC AP: 0.1 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

WB62™ Acrylic polymer-C, Acrylic resin (ts), Dipropylene glycol methyl ether, Quinacridone pigment, Water **GAL WT: 8.71 WT PCT SOLIDS: 17.93 VOL PCT SOLIDS:**
13.83 SOLVENT DENSITY: 8.30 VOC LE: 1.7 VOC AP: 0.3 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

WB63™ Dispersing agent, Perylene pigment, Polyurethane resin-A, Water **GAL WT: 8.71 WT PCT SOLIDS: 14.09 VOL PCT SOLIDS: 10.05 SOLVENT DENSITY: 8.32**
VOC LE: 1.2 VOC AP: 0.1 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE:
NO

WB64™ Acrylic resin (ts), Pigment red 202, Polyurethane resin-A, Quinacridone pigment, Water **GAL WT: 8.62 WT PCT SOLIDS: 12.72 VOL PCT SOLIDS: 9.51**
SOLVENT DENSITY: 8.33 VOC LE: 1.5 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

WB65™ Acrylic resin - waterborne, N-pentanol, Polyurethane resin-B, Water **GAL WT: 8.42 WT PCT SOLIDS: 12.59 VOL PCT SOLIDS: 11.06 SOLVENT DENSITY:**
8.28 VOC LE: 2.1 VOC AP: 0.3 FLASH POINT: 141 °F - 200 °F H: 0 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY
REACTIVE: NO

WB67™ Acrylic polymer-C, Acrylic resin (ts), Polyurethane resin-A, Quinacridone pigment, Water **GAL WT: 9.02 WT PCT SOLIDS: 27.99 VOL PCT SOLIDS: 21.84**
SOLVENT DENSITY: 8.29 VOC LE: 0.7 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

WB68™ Acrylic polymer-C, Acrylic resin (ts), Quinacridone pigment, Water **GAL WT: 8.68 WT PCT SOLIDS: 16.90 VOL PCT SOLIDS: 13.01 SOLVENT DENSITY: 8.30**
VOC LE: 1.4 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE:
NO

WB82™ Acrylic resin (ts), Dipropylene glycol methyl ether, Iron hydroxide, Polyurethane resin-A, Water **GAL WT: 9.31 WT PCT SOLIDS: 21.87 VOL PCT SOLIDS:**
12.52 SOLVENT DENSITY: 8.32 VOC LE: 2.0 VOC AP: 0.3 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

WB84™ Acrylic polymer-C, Acrylic resin (ts), Iron oxide, Polyurethane resin-A, Water **GAL WT: 9.38 WT PCT SOLIDS: 18.11 VOL PCT SOLIDS: 7.56 SOLVENT**
DENSITY: 8.30 VOC LE: 1.9 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

WB90™ 2-amino-2-methyl-1-propanol, Acrylic polymer-C, Acrylic resin (ts), Dipropylene glycol methyl ether, Isopropyl alcohol, Light yellow lemon yellow oxide pigment,
Rheology agent, Water **GAL WT: 8.99 WT PCT SOLIDS: 18.31 VOL PCT SOLIDS: 10.90 SOLVENT DENSITY: 8.28 VOC LE: 3.0 VOC AP: 0.6 FLASH POINT: 141 °F**
- 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

WB91™ 2-amino-2-methyl-1-propanol, Acrylic polymer-A, Iron oxide, Polyurethane resin-A, Water **GAL WT: 9.06 WT PCT SOLIDS: 20.66 VOL PCT SOLIDS: 13.64**
SOLVENT DENSITY: 8.32 VOC LE: 1.3 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

WB93™ Acrylic polymer-C, Acrylic resin (ts), C.i. pigment brown, Polyurethane resin-A, Water **GAL WT: 8.83 WT PCT SOLIDS: 21.46 VOL PCT SOLIDS: 16.53**
SOLVENT DENSITY: 8.31 VOC LE: 0.9 VOC AP: 0.2 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO

WB9900™ Acrylic resin - waterborne, Carbon black, hydroxy & 4-sulfophenyl-modified, sod, Dipropylene glycol methyl ether, N-pentanol, Water **GAL WT: 8.49 WT PCT**
SOLIDS: 22.67 VOL PCT SOLIDS: 20.49 SOLVENT DENSITY: 8.25 VOC LE: 1.9 VOC AP: 0.5 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA
TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

Footnotes:

TSCA: in compliance In compliance with TSCA Inventory requirements for commercial purposes.

ACGIH American Conference of Governmental Industrial Hygienists.

IARC International Agency for Research on Cancer.

NTP National Toxicology Program.

OSHA Occupational Safety and Health Administration.

PNOR Particles not otherwise regulated.

PNOC Particles not otherwise classified.

STEL Short term exposure limit.

TWA Time-weighted average.

* VOC less exempt (theoretical) and VOC as packaged (theoretical) are based upon the VOC of the packaged material at the point of manufacture.

All products denoted with TM or ® are trademarks or registered trademarks of E. I. du Pont de Nemours and Company or its affiliates.

* = Section 313 Supplier Notification: These chemicals are subject to the reporting requirements of Section 313 of the Emergency planning and Right-to-Know act of 1986 and of 40 CFR 372.

@ = Listed as a Clean Air Act Hazardous Air Pollutant.

= EPCRA Section 302 - Extremely hazardous substances.

Notice:

The information on this Material Safety Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process.

Product Manager: Refinish Sales

Prepared by: Y. B. Yarbrough